



16MA400

LOW DENSITY POLYETHYLENE

INJECTION MOULDING & MASTERBATCH RESIN

I6MA400 is an injection moulding grade film grade Low Density Polyethylene (LDPE) produced by high pressure tubular process. The high melt flow index makes it ideal for moulding of very thin, intricate and large items having adequate mechanical properties. This grade is also an ideal choice for making masterbatches with higher loading.

| Typical Characteristics* | | | |
|---------------------------------|-------------|-----------|-----------------|
| Property | Test Method | Unit | Typical Value** |
| Melt Flow Index (190°C/2.16 kg) | ASTM D1238 | gm/10 min | 30 |
| Density (23°C) | ASTM D1505 | gm/cm³ | 0.918 |
| Tensile Strength at Yield | ASTM D638 | MPa | 10 |
| Elongation at Yield | ASTM D638 | % | 40 |
| Flexural Modulus | ASTM D790 | MPa | 140 |
| Notched Izod Impact Strength | ASTM D256 | J/m | No Break |
| Vicat Softening Point | ASTM D1525 | °C | 84 |

^{*}Typical Characteristics and not to be taken as specifications

Applications

Masterbatches, powder coating, soft mouldings.

Regulatory Information

• Meets the requirements stipulated in standard IS: 10146-1982 on "Specification for Polyethylene for safe use in contact with foodstuffs, pharmaceuticals, and drinking water". It also conforms to the positive list of constituents as prescribed in IS: 10141-1982. The grade and the additives incorporated in it also comply with the FDA:CFR Title 21,177.1520, Olefin polymers.

Storage Recommendations

 $\bullet \ \ Bags \ should \ be \ stored \ in \ dry/closed \ \ conditions \ at \ temperatures \ below \ 50^{\circ}C \ and \ protected \ from \ UV/direct \ sunlight.$

^{**}Mechanical Properties are on Injection Moulded Specimen