

Bapolene® 2035

High Density Polyethylene Copolymer

Product Description

This resin is a high density polyethylene copolymer for blow molding applications. It is recommended for applications that require high top load strength and good ESCR properties. This product meets US FDA 21 CFR 177.1520.

General			
Material Status	 Commercial: Active 		
Features	Copolymer	High ESCR (Stress Crack Resist.)	High Strength
Uses	 Blow Molding Applications 	Containers	
Agency Ratings	• FDA 21 CFR 177.1520		
Processing Method	Blow Molding		
Revision Date	• 5/18/2018		

Physical	Typical Value	(English)	Typical Value	(SI)	Test Method
Density	0.955	g/cm³	0.955	g/cm³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.35	g/10 min	0.35	g/10 min	ASTM D1238
Environmental Stress-Cracking Resistance (ESCR)					ASTM D1693
100% Igepal	25.0	hr	25.0	hr	

Mechanical	Typical Value	(English)	Typical Value	(SI)	Test Method
Tensile Modulus - Tangent ²	185000	psi	1280	MPa	ASTM D638
Tensile Strength ³ (Yield)	4000	psi	27.6	MPa	ASTM D638
Tensile Elongation ³ (Break)	> 500	%	> 500	%	ASTM D638

Notes

For additional information, visit us at www.bambergerpolymers.com

Bamberger Polymers Two Jericho Plaza, Jericho, New York, 11753, U.S.A. Tel: 516-622-3600 Fax: 516-622-3620 Email: bpinfo@bapoly.com

© 2017 Bamberger Polymers. Bamberger Polymers does not guarantee the applicability or the accuracy of the information contained herein, nor the suitability of the products described herein for any particular purpose. The applicability of any Agency Rating described herein is subject to the processing or specific end use of the products. Bamberger Polymers shall not be responsible for any damage or injury resulting from any failure to follow appropriate industry standards, or from hazards inherent in the nature of the product and/or material, nor for toxicological effects or Industrial Hygiene associated with particular use of any product described herein. No warranties of any kind, either express or implied, are made with respect to the products described herein or with respect to the use of the products described herein. The user assumes all risk and liabilities in connection with such usage.

Bamberger Page: 1 of 1

¹ Typical properties: these are not to be construed as specifications.

² 3 Point Load

³ 2.0 in/min (51 mm/min)