



Lotrène Q 5502BN High Density Polyethylene Resin

DESCRIPTION AND USE

This high molecular weight hexene copolymer is tailored for lightweight blow molded containers that require:

- Excellent stiffness
- Exceptional processability
- Exceptional stress cracking resistance

Typical applications include:

- Ice chest & coolers
- Household & industrial chemical containers
- Food packaging & pharmaceutical containers
- Bleach & detergents containers

This resin meets these specifications:

- ASTM D4976 PE 235
- FDA 21 CFR 177.1520(c) 3.2a, use conditions B through H per 21 CFR 176.170(c)
- Listed in the Drug Master File

NOMINAL PHYSICAL PROPERTIES	ASTM	UNIT	VALUE
Density	D1505	g/cm3	0.955
Melt Index, Condition 190 °C/2.16 kg Condition 190 °C/21.6 kg	D1238 D1238	g/10min g/10min	0.35 33
ESCR Condition A, F ₅₀ (100% Igepal) Condition B, F ₅₀ (100% Igepal)	D1693 D1693	h h	45 35
Tensile Yield Strength, 50 mm/min	D638 Type IV	МРа	27
Elongation at Break, 50 mm/min	D638 Type IV	%	>600
Brittleness Temperature	D746	°C	<-75
Flexural Modulus, Tangent	D790	MPa	1370
Shore D Hardness	D2240	-	63

TECHNICAL DISCLAIMER

The values reported in this technical data sheet are the results of tests carried out in accordance with standard test procedures in a laboratory environment. Actual properties may vary depending on batch and extrusion conditions. Therefore, these values should not be used for specification purposes.

Before using this product, the user is advised and cautioned to make its own determination and assessment of the safety and suitability of the product for the specific use in question, and is further advised against relying on the information contained herein as it may relate to any specific use or application.

It is the ultimate responsibility of the user to ensure that the product is suitable for, and the information is applicable to the user's specific application. Muntajat does not make, and expressly disclaims, all warranties, including warranties of merchantability or fitness for a particular purpose, regardless of whether oral or written, expressed or implied, or allegedly arising from any usage of any trade or from any course of dealing, in connection with the use of the information contained herein or the product itself.

The user expressly assumes all risks and liabilities, whether based in contract, tort or otherwise, in connection with the use of the information contained herein or the product itself. Trademarks may not be used in any manner other than expressly authorized in a written agreement and no trademark or license rights of any kind are granted hereunder, by implication or otherwise.

